

### FEATURES AND BENEFITS

MEDITE TRICOYA EXTREME is characterised by its durability, dimensional stability and reliability properties. The new design and application possibilities offered by the marriage of acetylated wood fibre with the manufacturing technology of MEDITE MDF is set to excite and stimulate composite product manufacturers, designers, architects and the construction industry alike, opening up new possibilities and solutions.



#### DURABLE

Longer lasting, perfect for external and internal wet environments



#### 50 YEAR GUARANTEE

Peace of mind with a 25 year in-ground and 50 year above ground guarantee




#### ENHANCED STABILITY

Swelling and shrinking dramatically reduced



#### DESIGN FREEDOM

All the design, fixing and machining flexibility of MDF



#### LOWER MAINTENANCE COSTS

Extended periods between exterior coatings maintenance



#### PERFECT FOR COATING

Improved stability and durability enhances service life of the coating. Damaged coating will not affect the core



#### SUSTAINABLY SOURCED

FSC® certified. Wood used from sustainable sources



#### RESISTANT TO FUNGAL DECAY

Effective barrier to fungal decay



#### DESIRED SERVICE LIFE OF 60 YEARS

Independent testing by BRE shows an expected service life of 60 years for exterior use

### SUPPLY

MEDITE TRICOYA EXTREME is produced in the following standard panel size

- 6mm 1220 x 2440
- 9mm 1220 x 2440
- 12mm 1220 x 2440 / 3050
- 15mm 1220 x 2440 / 3050
- 18mm 1220 x 2440 / 3050

Other sizes may be produced upon request.

**Conditioning:** MEDITE TRICOYA EXTREME moisture content should be below 10% before processing and coating applications.

**Machining/Finishing:** MEDITE TRICOYA EXTREME may be cut, machined and used in exactly the same way as other wood fibreboards such as MEDITE PREMIER. There is no change in machinability. MEDITE TRICOYA EXTREME is delivered with a 120 grit sanded finish. It may be sanded with finer papers to achieve smoother surfaces. Water based paint systems may be used to decorate MEDITE TRICOYA EXTREME. MEDITE TRICOYA EXTREME may be successfully coated with melamine papers; laminates and foils. Exterior adhesives such as epoxy, polyurethane, phenol-resorcinol resin and EPI may be used conforming to EN301 Type I.

All mechanical fasteners that may be wetted, including screws, hinges, fixtures and fittings, should be manufactured from Stainless Steel EN 3506 type A2 or A4 or ANSI type 304 or 316. Internal handles and other furniture that are normally used in dry conditions may be made from any usually acceptable material.

**Fire rating:** MEDITE TRICOYA EXTREME is classified as Euroclass E within the Euroclassification system.

# EXTREME

**MEDITE**® 

## HIGH PERFORMANCE WOOD PANEL

### TECHNICAL SPECIFICATIONS

PROPERTY	RANGE	TEST METHOD	UNITS	THICKNESS				
				6	9	12	15	18
Density	+/-30		kg/m <sup>3</sup>	720	720	720	700	700
Internal Bond	Min	EN 319	N/mm <sup>2</sup>	0.80	0.80	0.80	0.80	0.80
Modulus of Rupture	Min	EN 310	N/mm <sup>2</sup>	30.0	30.0	25.0	20.0	20.0
Modulus of Elasticity	Min	EN 310	N/mm <sup>2</sup>	3,000	3,000	2,500	2,500	2,500
Screw Holding Face	Min	EN 320	N	-	-	-	900	900
Screw Holding Edge	Min	EN 320	N	-	-	-	700	700
Free Formaldehyde	Max	EN 120	mg/100g	< 1.0	< 1.0	< 1.0	< 1.0	< 1.0
Thickness Tolerance		EN 324-1	mm	+/- 0.15	+/- 0.15	+/- 0.15	+/- 0.15	+/- 0.15
Thickness Swell (24hrs)	Max	EN 317	%	2.5	2.0	2.0	1.5	1.5
Thermal Resistance		R Value	m <sup>2</sup> K/W	0.056	0.085	0.114	0.15	0.18
<b>DIMENSIONAL MOVEMENT</b>								
Length / Width		EN 318	%	+/- 0.1	+/- 0.1	+/- 0.1	+/- 0.1	+/- 0.1
Thickness		EN 318	%	+/- 1.0	+/- 1.0	+/- 1.0	+/- 1.0	+/- 1.0
<b>AFTER BOIL TEST</b>								
Internal Bond	Min	EN 319	N/mm <sup>2</sup>	0.65	0.65	0.65	0.65	0.65

QMS No. Tech 05.2012: The results as listed on left are based on the minimum specification requirements for MEDITE TRICOYA EXTREME manufactured by MEDITE EUROPE DAC. All parameters are in compliance with EN 622 parts 1 & 5. As part of the MEDITE EUROPE ongoing product development programme, the right to modify these product specifications without notice is reserved. No formaldehyde is added to the acetylated softwood fibres during manufacture of MEDITE TRICOYA EXTREME. Free formaldehyde is less than 1.0mg/100g using EN 120 test method, complying with the lower levels required by CARB phase 2.



UK: +44 (0) 1322 424900  
Ireland: +353 5 181 0205  
Germany: +49 32221097221  
France: +33 975189830  
Netherlands: +31 858886230  
Belgium: +32 28086256

[www.mdfosb.com](http://www.mdfosb.com)

MEDITE® is a registered trademark of MEDITE EUROPE DAC ("MEDITE") and cannot be used or reproduced without MEDITE'S written permission. Tricoya® and the trimarque device are registered trademarks owned by Accsys Technologies, the trading name of Titan Wood Ltd.

V11218

**MEDITE**®  
DEFINING THE STANDARD OF MDF