

## FibraPan® EZ Decor

### TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm						
			2.5-4	>4-6	>6-9	>9-12	>12-19	>19-30	>30-45
Density (*)	EN 323:1993	kg/m <sup>3</sup>	850-825	820-800	770-740	735-720	720-675	675-655	660
Internal Bond	EN 319:1993	N/mm <sup>2</sup>	0,90	0,85	0,7	0,65	0,55	0,55	0,55
Thickness Swelling 24h	EN 317:1993	%	35	30	17	15	12	10	8
Bending Strength	EN 310:1993	N/mm <sup>2</sup>	38	36	23	22	20	20	20
Surface Soundness	EN 311:2002	N/mm <sup>2</sup>	-	1,2	1,2	1,2	1,2	1,2	1,2
Formaldehyde emission	EN 717-1:2004	ppm	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05
Reaction to fire	EN 13501-1:2018	Euroclass	CWFT	CWFT	CWFT	CWFT	CWFT	CWFT	CWFT
Moisture Content	EN 322:1993	%	-	7+/-3	7+/-3	7+/-3	7+/-3	7+/-3	7+/-3

### TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm					
			4-6	>6-9	>9-12	>12-19	>19-30	>30-45
Thickness on Nominal Dimensions	EN 14323:2021	mm	+/-0,3 (Class 1) +0,5/-0,3 (Class 3A)	+/-0,3 (Class 1) +0,5/-0,3 (Class 3A)	+/-0,3 (Class 1) +0,5/-0,3 (Class 3A)	+/-0,3 (Class 1) +0,5/-0,3 (Class 3A)	+/-0,5	+/-0,5
Thickness within the Board (Max-min)	EN 14323:2021	mm	0,6	0,6	0,6	0,6	0,6	0,6
Length & Width	EN 14323:2021	mm	5	5	5	5	5	5
Flatness (Only in balanced coverings)	EN 14323:2021	mm/m	2 (**)	2 (**)	2 (**)	2 (**)	2 (**)	2 (**)

### COATING PROPERTIES

PROPERTIES	TEST METHOD	UNITS	SPECIFICATION
Surface Aspect	EN 14323:2021	Rating	4
Surface defects. Dots	EN 14323:2021	mm <sup>2</sup> /m <sup>2</sup>	2
Surface Defects. Lines	EN 14323:2021	mm/m <sup>2</sup>	20
Edges Damaged	EN 14323:2021	mm	10
Resistance to Scratching	EN 14323:2021	N	1,5
Resistance to Cracking	EN 14323:2021	Rating	3
Resistance to Staining (Groups 1 and 2)	EN 14323:2021	Rating	5
Colour resistance to UV light (Xenon lamp)	EN 14323:2021	Blue wool scale, n°	6
Antibacterial efficiency	ISO 22196	%	99,9

### RESISTANCE TO ABRASION

PROPERTIES	TEST METHOD	CLASS	IP NUMBER OF TURNS
Abrasion resistance. Designs	EN 14323:2021	1	< 50
Abrasion resistance. Unicolors and AH Products	EN 14323:2021	3A	≥ 350

(\*) Values to be considered as a rough guide only.

\*\* Thickness ≥ 15mm

These physical-mechanical values comply with upon the values established in European standard EN 622-5:2009, Table 3. - Requirements for general-purpose boards for use in dry conditions (Type MDF).

CWFT: Reaction to fire classification without the need of testing, according to European Commission Decision 2007/348/EC.

Product with very low formaldehyde emission ≤ 0.05 ppm (≤ 0.062 mg/m<sup>3</sup>) measured under European Standard EN 717-1:2004 that complies with the specifications of Class E1 defined in the EN 622-1:2003 European Standard.

Product compliant with US EPA TSCA Title VI and California Code of Regulation 17 ATCM 93120, Phase 2.

Product tested by IMSL under the Standard ISO 22196:2011, verifying that inhibits the growth and development of bacteria without affecting the characteristics of the coating.

## FibraPan® EZ Decor

The quality of this board is backed by AITIM's Quality Seal.

Reports and certificates relating to this product are available upon request.

### Handling/Storage Recommendations:

Boards should always be stored under cover and on a flat surface.  
Optimal storage conditions are 65% humidity; avoid environments that are either too dry or too damp.  
Under no circumstances should there be direct contact with water.  
Spacers must always be vertically aligned.  
Under no circumstances should boards be stacked more than 4 high.

If the packaging is damaged during handling, it must be re-packaged to ensure the product's proper preservation.

Failure to observe the stated stacking conditions, as well as changes in humidity or temperature in warehouses or processing areas, can lead to irreversible distortion and warping.

### PRODUCT SAFETY INFORMATION

The wood used by Finsa in the manufacture of fibreboards (MDF) is a variable mix composed mainly of pine and eucalyptus wood, and in the manufacture of its particleboards, a variable mix of wood, primarily pine and eucalyptus, as well as recycled wood, in which, due to its heterogeneous origin, it is not possible to determine the species that compose it.

In any case, it complies with Regulation (EU) 995/2010 (EUTR) and Regulation (EU) 2023/1115 (EUDR), applicable from January 1, 2027, and originates from legal sources, being controlled wood under PEFC and FSC criteria.

### Composition Information.

Wood-based panels contain:

Wood (various species, mainly pine and eucalyptus and, where applicable, recycled wood): 70 – 92 %

Water-based polymerized resins (UF, MUF, Phenolic, PVA, MDI, bio-resins): 8 – 25 %.

Paraffin emulsion and other additives: 0.5 – 7.0 %.

CLP: Wood-based panels are not affected by Regulation (EC) No 1272/2008 on classification, labelling and packaging of substances and mixtures (CLP).

### REACH:

Complies with Regulation (EU) 2023/1464, which amends Annex XVII to Regulation (EC) No 1907/2006 of the European Parliament and of the Council as regards formaldehyde (REACH).

It does not contain any substance classified as SVHC in concentrations exceeding 0.1% weight/weight according to the candidate list of the regulation itself.

### Recommendations for use:

The user/recipient (individual or entity) of the product is obliged to assess the risks to workers who will process/transform them based on local legal health and safety requirements, implementing the necessary controls to provide appropriate preventive measures: e.g., manual handling of loads, dust extraction in case of cutting/sanding/machining, use of personal protective equipment, etc..

### Exposure controls / Personal protection

#### Exposure controls:

During processing, the primary method for controlling airborne wood dust is local exhaust ventilation at the point of generation. Areas where processing takes place must be properly ventilated.

#### Personal protection:

Wood dust will be generated during processing. It is recommended to:

Wear appropriate respiratory protective equipment.

Wear gloves during handling.

Wear eye protection to prevent dust particles from entering the eyes.

#### Occupational Exposure Limit Values (OELs):

In accordance with the limits established in Spain for processes where wood dust may be generated, an Occupational Exposure Limit Value - Daily Exposure (VLA-ED / 8-hour TWA) of 2 mg/m<sup>3</sup> has been established. This value represents the average dust concentration limit in the air over an 8-hour shift.

This value is aligned with Directive (EU) 2019/983 (amending Directive 2004/37/CE).

In other countries, the applicable regulatory limits in force must be taken into account.