

Technical Data

Fibre Cement 6mm PrePrimed 1200x600mm

NoMorePly 6mm PrePrimed Fibre Cement Board is manufactured to improve strength in a timber floor prior to applying a final floor finish. It meets the performance requirements of BS EN 12467:2012 for Fibre Cement Flat Sheets.

Technical Data

Specification	
Board Weight	6.25kg
Tolerance	+/- 2%
Test Standard	BS EN 12467:2016 + A1:2016
Performance	
Density	1.28g cm ³
Linear Variation (change in moisture)	0.16%
Bending Strength (dry)	17.56 MPa
Bending Strength (saturated in warm water)	12.97 MPa
Water Impermeability (unprimed)	No water formation after 24 hours Damp patch covers tested area
Water Impermeability (primed)	No water formation after 24 hours No damp patch in tested area after 192 hours
Reaction to Fire Test Standard	Euro Class A1 Non-Combustible (A1fl) EN ISO 1182 & EN ISO 1716
Mechanical Characteristics - Bending Strength (MOR)	Class 2

Technical Data

Fibre Cement 6mm PrePrimed 1200x600mm

Technical Data Continued

Durability. Freeze-Thaw	Complied
Durability. Heat-Rain	Passed
Durability. Warm Water	Complied
Durability. Soak-Dry	Complied
U-Value	≤ 0.35
Thermal Conductivity	0.15651 W/mK
Thermal Resistance	0.04525 m2K/W