

Technical Data

9mm Fibre Cement Board 2400x1200mm

NoMorePly 9mm Fibre Cement Board is manufactured to improve strength for multiple application, internally and externally. It meets the performance requirements of BS EN 12467:2012 for Fibre Cement Flat Sheets.

Technical Data

Specification	
Board Weight	39.5kg
Tolerance	+/- 2%
Test Standard	BS EN 12467:2016 + A1:2016
Performance	
Density	1.28g cm ³
Linear Variation (change in moisture)	0.16%
Bending Strength (dry)	17.27 MPa
Bending Strength (saturated in warm water)	14.93 MPa
Reaction to Fire Test Standard	Euro Class A1 Non-Combustible (A1fl) EN ISO 1182 & EN ISO 1716
Mechanical Characteristics - Bending Strength (MOR)	Class 2

Technical Data

9mm Fibre Cement Board 2400x1200mm

Technical Data Continued

Durability. Freeze-Thaw	Complied
Durability. Heat-Rain	Passed
Durability. Warm Water	Complied
Durability. Soak-Dry	Complied
Compression Strength	14.42 MPa
Thermal Conductivity	0.13381 W/mK
Thermal Resistance	0.07324 m2K/W