

JINLUN Woods' JADE 72 PLYWOOD		
products	JADE 72 Plywood	
Core:	Eucalyptus	
Glue:	PF	
Surface:	Eucalyptus grandis for Face/back	
Size:	3.6mm/5.5mm/9mm/12mm/15mm/18mm/25mm x1220x2440	
Density:	About 630KGS/M ³	
Tolerance of Thickness	“+/-0.5mm	
Tolerance of L/W	“+/-1mm	
Number of Layers	3/3/5/5/7/9/11 layers	
Moisture:	9-13%	
Formaldehyde Emission Class	class E1 (0.12mg/L - 0.17mg/L)	
Ultimate shearing strength	No less than 1.0Mpa	
Abrasion	≤0.1G.100G	
Impulsion	65KG/M ²	
Modulus of Elasticity	≥5000Mps （Average data）	
Bending Strength	≥30Mps	
Expansion Rate of thickness	≤6% （after 24 hours cold water）	
Bonding quality	≥1.5Mpa or Wood failure 100%(after 24h cold water); ≥1.2Mpa (after 4h bolling+16h drying+4h bolling);≥1.0Mpa (after 72h bolling)	
Application:	Construction,stage plywood,truck floor,container floor,package,and other Non slip place	